



YUPO® FPG-095 Specification Sheet

50 lb. Text

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	95 +/- 5	JIS P-8118	2
Basis Weight, Average	g/m2	73.2 +/- 4.0	JIS P-8124	2
Opacity, Average	%	90.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	20 +/- 4	TAPPI T-480	2
- Back	%	20 +/- 4	TAPPI T-480	2
Whiteness, Average	WI	96.0 +/- 2.0	JIS L-1015	2
Surface Resistivity - Top	log(Ω/\square)	12.0 max.	ASTM D257	2
- Back	log(Ω/\square)	12.0 max.	ASTM D257	2
Tensile Strength - MD	kgf/15mm	5.5 min.	TAPPI T-494	2
- TD	kgf/15mm	14.5 min.	TAPPI T-494	2
5% Elongation - MD	kgf/15mm	2.8 +/- 1.0	TAPPI T-494	2
- TD	kgf/15mm	6.9 +/- 2.0	TAPPI T-494	2
Tear Strength - MD	gf	33.5 +/- 8.5	TAPPI T-414	2
- TD	gf	17.5 +/- 8.5	TAPPI T-414	2
Clark Stiffness - MD	s-value	18.0 min.	TAPPI T-451	1, 2
- TD	s-value	41.0 min.	TAPPI T-451	1, 2

Notes Key:

- 1 - Stiffness increases with aging over the first month from date of manufacture.
- 2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FPG-095. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.