



# YUPO® FPG-150 Specification Sheet

## 78 lb. Text

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	150 +/- 8	JIS P-8118	2
Basis Weight, Average	g/m2	115.5 +/- 5.0	JIS P-8124	2
Opacity, Average	%	95.0 min.	TAPPI T-425	2
Gloss, Average - Top	%	20 +/- 4	TAPPI T-480	2
- Back	%	20 +/- 4	TAPPI T-480	2
Whiteness, Average	WI	96.0 +/- 2.0	JIS L-1015	2
Surface Resistivity - Top	log( $\Omega/\square$ )	12.0 max.	ASTM D257	2
- Back	log( $\Omega/\square$ )	12.0 max.	ASTM D257	2
Tensile Strength - MD	kgf/15mm	9.0 min.	TAPPI T-494	2
- TD	kgf/15mm	25.0 min.	TAPPI T-494	2
5% Elongation - MD	kgf/15mm	4.4 +/- 1.4	TAPPI T-494	2
- TD	kgf/15mm	12.0 +/- 3.0	TAPPI T-494	2
Tear Strength - MD	gf	63.0 +/- 17.0	TAPPI T-414	2
- TD	gf	31.0 +/- 11.0	TAPPI T-414	2
Clark Stiffness - MD	s-value	48.0 min.	TAPPI T-451	1, 2
- TD	s-value	106.0 min.	TAPPI T-451	1, 2

### Notes Key:

- 1 - Stiffness increases with aging over the first month from date of manufacture.
- 2 - Specification range shown

\* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for FPG-150. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.