



YUPO® TPRB-090 Specification Sheet Solvent-Resist Translucent Grade

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	90 +/- 6	JIS P-8118	2
Basis Weight, Average	g/m2	91.4 +/- 6.0	JIS P-8124	2
Opacity, Average	%	46.0 max.	TAPPI T-425	2
Gloss, Average - Top	%	53 +/- 8	TAPPI T-480	2
- Back	%	53 +/- 8	TAPPI T-480	2
Whiteness, Average	WI	86.0 min.	JIS L-1015	2

Notes Key:

2 - Specification range shown

* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for TPRB-090. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

TPRB-090, version 1, 2008-Aug-05