



# YUPO® QJJ-400 Specification Sheet

## 144 lb. Cover

<u>Parameter</u>	<u>Units</u>	<u>Range</u>	<u>Reference*</u>	<u>Notes</u>
Thickness, Average	micron	400 +/- 25	JIS P-8118	2
Basis Weight, Average	g/m2	390.0 +/- 24.0	JIS P-8124	2
Opacity, Average	%	94.5 min.	TAPPI T-425	2
Gloss, Average - Top	%	21 +/- 6	TAPPI T-480	2
- Back	%	21 +/- 6	TAPPI T-480	2
Whiteness, Average	WI	93 min.	JIS L-1015	2

### Notes Key:

2 - Specification range shown

\* Yupo test methods based on, but not necessarily the same as, reference stated; Yupo procedure stated if reference not available.

This document provides our current specifications for QJJ-400. Changes to these items may occur at the sole discretion of Yupo Corporation America. This issue supersedes any and all previous versions.

QJJ-400, version 2, 2008-Aug-05